

Outer Shell Fabric and Finish	Condition	Direction	Indices of Penetration, Repellency, Absorption			Flame Resistance	
			I_P	I_R	I_A	Average Afterflame (s)	Average Char Length (mm)
KNM220P(Rambo) with Moisture Wicking finish	Fuel Contamination	Warp	90.6	37.5	45.1	3.5	12.3
		Fill	98.6	27.1	51.2	6.3	13.0
	Fuel Contamination followed by Cleaning	Warp	48.6	34.6	44.5	0.0	16.3
		Fill	96.5	36.3	48.7	0.0	17.0
	As Received	Warp	N/A	N/A	N/A	0.0	16
		Fill	N/A	N/A	N/A	0.0	14
	After 5 Launderings	Warp	N/A	N/A	N/A	0.0	18
		Fill	N/A	N/A	N/A	0.0	19